

DATA SHEET – FLAME RETARDANT PINE PLYWOOD B-s1, d0

It is a plywood made of pine wood veneers with increased fire resistance. Intended for use in exterior conditions (according to PN-EN 636), meets the requirements of bonding quality class 3 according to PN-EN 314-2. The product has been classified in the reaction to fire class B-s1, d0 according to PN-EN 13501-1.

Types of plywood depending on the type of bonding:

- intended for use in exterior conditions (according to PN-EN 636), meeting the requirements of the 3rd class of bonding according to PN-EN 314-2

Types of plywood depending on quality class:

Plywood is produced in the following quality classes: I, II, III, IV (according to EN 635-3), where class I is the highest class and class IV - the lowest.

Thickness and tolerances

Plywood is produced with a thickness of min. 12 mm. Thickness tolerances are defined in the standard EN 315.

Humidity

10±5% (according to PN-EN 322).

Density

600 – 720 kg/m³ (according to PN-EN 323).

Standard formats

2500x1250mm, 1250x2500mm, 2440x1220mm, 1220x2440mm, 2130x1250mm, 1250x2130mm or as agreed with the customer.

Length and width tolerance: ± 3,5 mm (according to EN 315).

Edge straightness: ± 1,0 mm/m of side length (according to EN 315)

Processing options:

Cutting into smaller formats; simple and profile processing of edges,

Application:

Construction, walls, ceilings. The material can be mechanically fastened to wooden slats, with vertical and / or horizontal joints and with a ventilated or non-ventilated air gap.

